

BRONCE AL ALUMINIO

	Elementos				Esfuerzo a la tensión					% Alargamiento en 50mm					Dureza Brinell 3000Kg.					Dureza Rockwell (cifras nominales)					Conduc. Termica C.GS	
	Cobre	Aluminio	Fierros	Otros	Arena	Centr.	Extrs.	Lamina	Placa	Arena	Centr.	Extrs.	Lamina	Placa	Arena	Centr.	Extrs.	Lamina	Placa	Arena	Centr.	Extrs.	Lamina	Placa		
AMPCO 16	Resto	10.1	3.3	0.50	13.2	14.4				33	35				153	170				82B	87B				7.50	0.14
AMPCO 18	Resto	10.5	3.5	0.50	13.2	15.4	15			38	40	52			179	183	192			89B	90B	92B			7.45	0.15
AMPCO 18-13	Resto	10.5	3	0.50	13.2	14.7				34	36				166	170				86B	88B				7.45	0.15
AMPCO 18-22	Resto	10.5	3.5	0.50	15.4	16.9				54	58				223	228				97B	98B				7.45	0.15
AMPCO 18-23	Resto	10.5	3.5	0.50	15.4	16.2				52	55				202	207				94B	95B				7.45	0.15
AMPCO 20	Resto	11.3	3.8	0.50	12.5	14.7				40	42				212	223				96B	97B				7.36	0.11
AMPCO 20-13	Resto	11.3	3.8	0.50	12.5	1.7				36	39				202	212				94B	96B				7.36	0.12
AMPCO 21	Resto	13.1	4.4	0.50	11	11.8	16			55	55				285	285	302			29B	29B				7.20	0.11
AMPCO 22	Resto	14.1	4.7	0.50	12.5	12.5				70	70				331	331				35C	35C				7.06	0.10